

PRODUCT DATA **HARD HAT® Heat Resistant Coating- Brush Version**

DESCRIPTION

HARD HAT® 1015 and 1078 are Heat Resistant Coatings based on a silicone modified alkyd resin.

RECOMMENDED USES

HARD HAT® Heat Resistant Coating can be applied on new, bright or shot-blasted steel or well pre-treated coated surfaces such as barbecues, boiler fittings, hot air cannons, exhausts, etc.

HARD HAT® Heat Resistant Coating is intended for small maintenance jobs and repairs.

HARD HAT® Heat Resistant Coating provides protection up to a dry heat of 750°C (short-term peak load) for applications indoors or in a sheltered outdoor environment.

TECHNICAL DATA

Appearance: Satin Gloss
Colour: 1015: Aluminium / 1078: Black
Solids: Aluminium: 47% volume / Black: 40% volume
Recom. film thickness: 35-40 µm dry, equals 85 µm wet

VOC-content: 1015: 458 g/l max / 1078: 416 g/l max
Ready-for-use mixture: 1015: 458 g/l max / 1078: 416 g/l max
Category: A/i
EU Limit values: 600 g/l (2007) / 500 g/l (2010)

Drying times 20°C/50% r.v.
To touch: 2 hrs
To handle: 8 hrs
To recoat: 24 hrs
Full hardness: 24 hours after the minimum service temp of 150°C is reached.
Gradually heat the coating to 150°C (max. 50°C/hour)

Heat resistant: Standard 600°C (dry heat) / Short term peak 750°C (dry heat)

Coverage

Theoretical: 10-12 m² per litre at 35 - 40 µm dry.
Practical: Practical coverage depends on many factors such as porosity and roughness of the substrate and material losses during application. (see DIN 53220).

SURFACE PREPARATION

Remove grease, oil, dirt, loose rust, loose coatings and any other contamination using suitable agents. Sand intact old paintwork in order to roughen the surface slightly. The surface must be clean and dry during application.

DIRECTION FOR USE

To ensure homogeneity, coating materials should be thoroughly stirred prior to use.

MIXING AND THINNING

Brush: No thinning

Roller: No thinning. Use shorthaired polyamide (perlon 8 - 12 mm) rollers.

Clean up With RUST-OLEUM thinners 7301.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com

PRODUCT DATA **HARD HAT® Heat Resistant Coating- Brush Version**

APPLICATION CONDITIONS

Only apply if the air and surface temperatures are between 5 and 35°C and the relative humidity is less than 85%.

The temperature of the coated surface must be at least 3°C above the dew point.

REMARKS

RUST-OLEUM Heat resistant coating 1015 and 1078 are self-priming and should not be applied on primers or coatings, which are not heat resistant.

SAFETY

Consult Safety Data Sheet and Safety information printed on the can.

SHELF LIFE / STORAGE CONDITIONS

5 years from date of production in unopened cans, if stored in dry, well ventilated areas, not in direct sunlight at temperatures between 5° and 35°C.

Rust-Oleum Netherlands B.V.

Braak 1, 4704 RJ
P.O. Box 138, 4700 AC
Roosendaal, The Netherlands
T +31 (0)165 593 636
F +31 (0)165 593 600
info.nl@ro-m.com
www.ro-m.com

N.V. Martin Mathys S.A.

Kolenbergstraat 23
B - 3545 Zelem
Halen, Belgium
T +32 (0)13 460 200
F +32 (0)13 460 201
info.be@ro-m.com
www.ro-m.com

Rust-Oleum France S.A.S

11, Rue Jules Verne, B.P. 60039
95322 St-Leu-la-Forêt Cedex
France
T +33 (0)130 400 044
F +33 (0)130 409 980
info.fr@ro-m.com
www.ro-m.com

Rust-Oleum UK Ltd.

Unit 6, Spitfire Close
Coventry Business Park
Coventry, CV5 6UR
United Kingdom
T +44 (0)2476 717 329
F +44 (0)2476 718 930
info.uk@ro-m.com
www.ro-m.com

Rust-Oleum Mathys Italia s.r.l.

Largo Donegani 2
20121 Milano, Italia
T +39 335 10 93 482
info.it@ro-m.com
www.ro-m.com