

TECHNICAL HEALTH AND DATA SHEET

PRODUCT:- CHLORINATED RUBBER PAINT

REFERENCE:- G149/1

COLOUR:- WHITE,BLACK,BLUE 18.E.51
OTHER COLOURS TO SPECIAL
ORDER

FINISH:- GLOSS

TYPE:- CHLORINATED RUBBER

TYPICAL SG:- 1.23 @ 20°C

TYPICAL VISCOSITY:- 3.0 POISE @ 25°C

TYPICAL TOTAL SOLIDS:- 51% BY WEIGHT
27% BY VOLUME

TYPICAL FLASH POINT:- 40°C

RECOMMENDED THINNERS:- V607/15

APPLICATION:- BY BRUSH OR AIRLESS SPRAY

*COVERAGE GUIDE:- 11 SQ. METRES PER LITRE

*DRYING TIME:- SURFACE DRY - 2 HOURS
THROUGH DRY - 24 HOURS

VOC:- 599 g/litre

HEALTH & SAFETY:- SEE SHEET HSD 'K'

*BY BRUSH TO A DRIED FILM THICKNESS OF 20-25 MICRONS AT 20°C.

Issued October 2004

Teamac® Paints

**MANUFACTURERS OF DECORATIVE, MARINE AND INDUSTRIAL
COATINGS**

Teal & Mackrill Limited,
Lockwood Street, HULL. HU2 OHN
Telephone: 01482-320194 Fax: 01482-219266