

F10

FLEETWOOD UNDERCOAT

CHARACTERISTICS

A top quality alkyd based undercoat.

COLOUR

White and selected colours from Colour Answers Tinting Machine.

DRYING SCHEDULE

To Touch:- 15-30 mins

Tack Free:- 1 hr normal drying conditions.

Hard Dry:- Overnight

Dry to sand:- Overnight

Dry to recoat:- Overnight

SPECIFIC GRAVITY

1.48+/-0.10

WEIGHT SOLIDS

75+/-2%

VOLUME SOLIDS

53+/-2%

VEHICLE TYPE

Soya Bean Oil

FLASH POINT

105F

PRECAUTIONS

Keep out of reach of children.

Ensure good ventilation during application and drying.

In case of contact with eyes rinse immediately with plenty of water.

To remove splashes from skin use soap and water or a recognised skin cleaner. Do not take internally.

Contains no added lead.

APPLICATION

SPREADING RATE

(Calculated) 12-14m²

(125-145 sq ft) per litre.

METHODS

Brush, roller, conventional airspray.

PERFORMANCE INFORMATION

This product is a premium quality undercoat, formulated to be used over primed or previously painted surfaces. It has excellent holdout properties, obliteration, flow, sanding and application characteristics.

CLEAN UP

Clean equipment with White Spirits.

SURFACE PREPARATION

Surfaces must be clean, dry and free from dirt, chalk, grease, wax and dust. Remove all loose and flaking material. Scuff sand glossy surfaces. Spot prime any bare or new surfaces with the appropriate primer.

Stir thoroughly before use. Ideal preparation for a beautiful gloss finish. The Undercoat can be applied over properly prepared surfaces as above. Leave overnight to dry before overcoating.

Steel:- Remove all loose rust, peeling paint, other loosely adhering contaminations per SSPC SP2. Hand tool cleaning. Remove any contamination before applying subsequent coats of material. Prime base steel with an appropriate anti-corrosive primer.